

UDOT Minimum Sampling and Testing Requirements

Specification - Material: 02787 Bonded Wearing Course

Assurance: Sieve Analysis

Reference: AASHTO T 30

Lot Size: Production Day

Frequency per Lot: Four - If at least three samples cannot be taken, combine test results with the next day of production. Take one sample for each 15,000 yards or portion thereof from the following day's production.

Point of Acceptance: Plant

Sampling Reference: MOI 984
MOI 981

Report/Form: Materials Database

Assurance: Asphalt Binder Content

Reference: AASHTO T 308

Lot Size: Production Day

Frequency per Lot: Four – If at least three samples cannot be taken, combine test results with the next day of production. Take one sample for each 15,000 square yards of portion thereof from the following day's production.

Point of Acceptance: Plant

Sampling Reference: MOI 984
MOI 981

Report/Form: Materials Database
