

## UDOT Minimum Sampling and Testing Requirements

### *Specification - Material: 02712 Lean Concrete Base Course*

**Assurance:** Sieve Analysis

**Reference:** AASHTO T 27 / T 11

**Lot Size:** Paving Day

**Frequency per Lot:** One per stockpile

**Point of Acceptance:** Project stockpile

**Sampling Reference:** AASHTO T 2

**Report/Form:**

---

**Assurance:** Thickness

**Reference:** Thickness, determined by three measurements on each core (using a tape measure), recorded to 1/8 in. and averaged.

**Lot Size:** Project

**Frequency per Lot:** One core per 12000 sq. ft. Final areas less than 6000 sq. ft. will be added to the previous section. Final section over 6000 sq. ft. will constitute a separate area. Hand placements are considered separately. One core per placement area.

**Point of Acceptance:** Finished pavement

**Sampling Reference:** Randomly sampled according to AASHTO T 24

**Report/Form:**

---